



TECHNICAL PAINT SERVICES

A110 FORAMEL FINISH

Features:

A high build, quick drying synthetic finish providing a durable water and weather resistant coating for plant, machinery and the inside of marine tanks, being resistant to seawater and dry cargoes.

Availability:

BS4800 colour range and Clear in 5, 2.5 and 1 Litre containers.

Volume Solids:

50% ± 3% (BS 3900 Part A10).

Preparation:

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease. Ferrous and non-ferrous substrates should be treated with UP89 or UP90 Two Pack Etching Primer, followed by AP79 or AP80/20 Universal Primer before the application of A110. Existing paintwork should be degreased, flatted and coated with AP79 Universal Primer before finishing with A110.

Application:

By brush, conventional or airless spray. Supplied ready for use for brushing. Thin up to 20% by volume with UTR112 Universal Synthetic Thinners to achieve a spraying viscosity of 25 - 35 seconds BSB4 cup @ 20°C.

Coverage:

Approximately 40 metres per 5 Litres @ 25 microns dry film thickness.

Drying:

Touch dry: 1 hour @ 20°C.

Hard dry: 2 - 4 hours @ 20°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.