



TECHNICAL PAINT SERVICES

A146/60 SOLAR REFLECTING BITUMINOUS HEAVY BODIED

Features:

A high build, solar reflecting and water proofing bituminous aluminium coating designed for use as a finishing coat over bitumen and concrete roofing and primed steel. May be used as a base coat for A146/61 Solar Reflecting Aluminium to increase build and protection.

Availability:

In 5, 2.5 and 1 Litre containers.

Volume Solids:

60% ± 3% (BS 3900 Part A10).

Preparation:

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease.

Application:

Brush, roller, or conventional spray. Thinning is not normally required. Use X156 White Spirit for cleaning.

Note:

Some difference in brightness and general appearance may be anticipated between brush, roller and spray application, and therefore mixed methods of application are not recommended.

Coverage:

Approximately 35 - 40 sq metres per 5 Litres per coat.

Drying:

Touch dry: 2 hours @ 20°C.

Recoatable: 12 hours @ 20°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.