



TECHNICAL PAINT SERVICES

F42 FLUORESCENT FINISH

Features:

A special range of vivid safety marking paints, ideal for use in poorly lit areas. Suitable for application to wood and metal substrates. Requires a source of daylight, moonlight or artificial light to be effective.

Availability:

Yellow, Orange, Red, Blue, Green and Magenta Pink in 5, 2.5 and 1 Litre containers.

Volume Solids:

48% ± 3% (BS 3900 Part A10).

Preparation:

The substrate must be thoroughly clean, dry and free from dust and grease. Apply over FP42/5 Fluorescent Undercoat White.

Application:

By conventional spray. Thin up to 25% by volume with FTR42 Fluorescent Thinners to achieve a viscosity of 25 - 30 seconds BSB4 cup @ 20°C. For optimum durability, a coat of FL42/70/1 Fluorescent Overcoat Clear Varnish should be applied over the finish colour.

Coverage:

Approximately 8 - 12 sq metres per Litre depending on surface profile.

Drying:

Touch dry: 30 minutes @ 20°C.

Overcoat time: 2 hours @ 20°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.